

UNTREATED FUMED SILICA



CAB-O-SIL® PTG



CAB-O-SIL® PTG untreated fumed silica is a synthetic, amorphous, colloidal silicon dioxide that is generally regarded as unique in industry because of its unusual particle characteristics. CAB-O-SIL® fumed silica's extremely small particle size, its enormous surface area, its high purity, and its chain-forming tendencies set it apart in a class of its own. CAB-O-SIL® fumed silica is a light, fluffy powder that is white in appearance and is used in many applications and a variety of industries.

Product Form

Powder

Typical Properties

B.E.T. Surface Area	200 m ² /g
pH (4% aqueous slurry)	3.7–4.3
325 Mesh Residue (44 microns)	0.02% max.
Bulk Density* (Pour Density)	3.0 lb/ft ³ max. (50 g/l Tap Density)
Loss on Heating*	< 1.5% max.
Loss on Ignition* (@ 1000°C)	< 2 wt. %
Specific Gravity Wt. per gallon	2.2 g/cm ³ 18.3 lb
Refractive Index	1.46
X-ray Form	Amorphous
Assay (% SiO ₂)	> 99.8
Oil Adsorption	~350 (M-5) g/100 g oil
Average Particle (Aggregate) Length	0.2–0.3 microns

*At time of packaging.





Functions

Rheology Control
Reinforcement
Free Flow
Suspension
Adsorbant

Applications

Adhesives & Sealants
Coatings
Composites
Cosmetics
Foods
Inks
Pharmaceuticals

Packaging Options

CAB-O-SIL® fumed silicas are packaged in color-coded, multi-wall Kraft paper bags. Grade PTG is packaged in North America in 10-lb bags. The bags are unitized and sized to provide product protection, facilitate efficient handling, and maximize payloads. Specific information regarding standard and custom packaging may be obtained by contacting a sales service representative at the Cabot Corporation office in your region.

MSDS

A Material Safety Data Sheet for this product may be obtained by contacting the Cabot Corporation office in your region or visiting our website.

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

NORTH AMERICA

Cabot Corporation
Business and Technical Center
157 Concord Road
Billerica, MA 01821-7001
USA
Customer Service:
Phone: (800) 526-7591
Technical Service:
Phone: +1 (978) 663-3455
Phone: (800) 462-2313
Fax: +1 (978) 670-6167

EUROPE

Cabot
Interleuvenlaan 15 I
B-3001 Leuven
BELGIUM
Tel: +32 16 39 24 00
Fax: +32 16 39 24 44

ASIA/ PACIFIC

Cabot Specialty Chemicals
Level 21 MNI Tower 2
11, Jalan Pinang
50450 Kuala Lumpur
MALAYSIA
Phone: +60 3 2164 8352
Fax: +60 3 2161 0253

Cabot Specialty Chemicals
Shiba Boat Bldg. 5F
3-1-15 Shiba, Minato-ku
Tokyo 105-0014
JAPAN
Phone: +81 3 3457 7354
Fax: +81 3 3457 7658

SOUTH AMERICA

Cabot Latin America Division
Rua do Paraíso, 148 - 5º andar
CEP 04103-000, São Paulo
SP BRAZIL
Customer Service:
Phone: +55 11 2144 6400
Fax: +55 11 3253 0051

MIDDLE EAST/ AFRICA

Cabot Specialty Chemicals
Jebel Ali Free Zone
LOB 15, Office 424
Dubai
UNITED ARAB EMIRATES
Phone: +971 4 8871 800
Fax: +971 4 8871 801